

ARTS Energy's VHT high temperature Ni-MH series are perfectly suited to professional applications requiring a battery with an exceptional robustness. It is designed to operate in very demanding environment.

The VHT 7/5 Cs has been designed to offer a very long life duration in a wide range of temperature.

In ELU the VHT 7/5 Cs will offer more than 4 years life at 40°C permanent temperature (T type cell).

In back up applications, the VHT 7/5 Cs will offer 5 to 10 years life.

In cycling application (solar, peak shaving), the VHT 7/5 Cs will offer 5 to 10 years life in an environment from -40°C to +85°C. It delivers for example, 5000 cycles at 50% DOD.

To meet customers' requirements, ARTS Energy provides custom-designed and standardised battery packs.

For applications below -20°C and above +60°C, please contact ARTS Energy to confirm the optimum battery design, and to agree the usage profiles.

№ APPLICATIONS

- Emergency lighting (ELU)
- Back-up systems
- Peak shaving applications (money saving)
- Professional electronics
- Solar

MAIN BENEFITS

- Very high cycle life
- Exceptional temperature range
- Superior robustness

👷 TECHNOLOGY

- Foam positive electrode
- Plastic bonded metal-hydride negative
- electrode

	+ ENERSY NIF-MIH VHT 7/5 Cs HRMT 23/62 1.2V - 4Ah	
ELECTRICAL CHARACTERISTICS	5	
Nominal voltage (V)		1.2
Typical capacity (mAh)*		4200
IEC minimum capacity (mAh)*		4000
IEC designation		HRMT 23/62
Impedance at 1000 Hz (mΩ)		20
* Charge 16 h at C/10, discharge at C/5.		
DIMENSIONS		22.0 + 0.05
Diameter (mm)		22.0 ± 0.05
Height (mm)		60.0 ± 0.3
Top projection (mm)		0.8 ± 0.2
Top flat area diameter (mm)		9.0
Weight (g) Dimensions are given for bare cells.		74
CHARGE CONDITIONS	Tomp (9C)	Current
	Temp. (°C)	
ELU applications	0 to + 40	Intermittent permanent, consult ARTS Energy
Back up applications	-20 to +85	Consult ARTS Energy
Solar applications	-40 to +85	C/3 max
DISCHARGE CONDITIONS	Temp. (°C)	Current
	+20 to +85	3C max
	0 to +85	C/2 max
	-20 to +85	C/5 max
	-40 to +85	C/20 max
CYCLING CONDITIONS	Cycling	Life duration
ELU applications	1 discharge/month max	4 years
Back up applications	1 discharge/day max	5 to 10 years
Solar applications	1 discharge/day max	5 to 10 years

NI-MH

VHT 7/5 Cs High Temperature Series


VHT 7/5 Cs

High Temperature Series

STORAGE

Recommended: + 5°C to + 25°C Relative humidity: 65 ± 5 %

MI TYPICAL DIMENSIONS




Typical dimensions (mm). Without tube.


The operation of the battery must strictly be in accordance with ARTS Energy technical recommendations, to obtain the performances stated by ARTS Energy.

Data is given for single cells. Please consult ARTS Energy for utilisation of cells outside specification.


Data in this document is subject to change without notice and become contractual only after written confirmation by ARTS Energy.


For graphs shown, C is the IEC_s capacity





Discharge at C/10 at different temperatures after charge at C/10 at different temperatures







10, rue Ampère Zone Industrielle - 16440 Nersac, France Tél. +33(0)5 45 90 35 52 /35 53 contact@arts-energy.com

Doc No.: 024-B-0418 - Edition: April 2018 ARTS Energy SAS. Stock capital 971.002 RCS Angoulême 792 635 013 Conception in FR by Alain Bruneaud Création



www.arts-energy.com